S1141

(ANSI:FR-4)UV Blocking

特点

- UV Blocking和 AOI兼容,可提高PCB生产效率。

- 优良的耐热性。优良的尺寸稳定性。优秀的机械性能和电性能。

FEATURES

- UV Blocking and AOI compatible, so as to Increase productivity.
- Good soldering reliability.
- Good dimensional stability.
- Excellent mechanical and electrical properties.

应用领域

电脑、仪器仪表、摄象机、通讯设备、 电子游戏机等。

APPLICATIONS

Computer, Instrumentation, VCR, Communication equipment, Electronic game machine, etc.

GENERAL PROPERTIES

Test Item	Treatment Condition	Unit	Property Data	
			SPEC	Typical Value
	DSC		130	140
Flammability	C-48/23/50	-	V-0	V-0
	E-24/125			
Volume Resistivity	After moisture resistance	M -cm	10 ⁶	5 × 10 ⁸
	E-24/125		10 ³	5 × 10 ⁶
Surface Resistance	After moisture resistance	M	10 ⁴	5×10^{7}
	E-24/125		10 ³	5 × 10 ⁶
ance	D-48/50+D-0.5/23	S	60	120
Breakdown	D-48/50+D-0.5/23	KV	40	60
Constant (1MHz)	C-24/23/50	-	5.4	4.6
n Factor (1MHz)	C-24/23/50	-	0.035	0.015
Unetched Etched	288 ,20s	-	No delamination	No delamination
Peel 1oz Strength Cu. Foil	288 ,10s	N/mm	1.05	1.8
	125		0.70	1.6
LW	А	MPa	415	600
CW			345	500
orption	D-24/23	%	0.35	0.15
Before Tg	TMA	μm/m	-	55
After Tg	TMA	μm/m	-	260
ΓΙ	IEC-112 Method	V	-	175
	esistivity esistance ance breakdown Constant (1MHz) n Factor (1MHz) Unetched Etched 1oz Cu. Foil LW CW orption Before Tg After Tg	DSC	DSC	Treatment Condition

Specimen Thickness:1.6mm

Explanations: C = Humidity conditioning;

D = Immersion conditioning in distilled water; E = Temperature conditioning.

The figures following the letter symbols indicate with the first digit the duration of the preconditioning in hours, with the second digit the preconditioning temperature in and with the third digit the relative humidity.